



- **EPDM-CR RITARDANTE DI FIAMMA UL94 HBF**
EPDM FLAME RETARD UL 94 HBF
- **OTTIMA RESISTENZA ALLE ALTE TEMPERATURE ED AGLI AGENTI ATMOSFERICI CON PROPRIETÀ DI RESISTENZA ALLA FIAMMA**
EXCELLENT RESISTANCE TO HIGH TEMPERATURES AND ATMOSPHERIC AGENTS, WITH FLAME-RETARDANT PROPERTIES



CAMPI D'IMPIEGO APPLICATIONS

- Automotive
- Riscaldamento-condizionamento
- Ferroviario
- Costruzioni (infissi-isolamento)
- Aerospaziale
- Navale
- Macchine movimento terra
- Macchine Utensili
- Elettrico
- Fotovoltaico
- Energia Eolica
- Energia Elettrica
- Sportivo
- Anti-infortunistica
- Automotive
- Heating-conditioning
- Railway
- Construction (fixtures-insulation)
- Aerospace
- Naval
- Constructions equipment
- Machine tools
- Electric
- Photovoltaic
- Wind energy
- Electric energy
- Sporty
- Safety



FORMATI DISPONIBILI AVAILABLE FORM



Rotoli / Rolls



Placche / Sheets



Profili / Profiles



Barre / Bars



SPECIFICHE TECNICHE TECHNICAL DATA SHEET

	NORME / STANDARD	VALORE / RESULTS
 Tipologia Materiale Material Base		EPDM/CR
 Struttura cellulare Cells structure		Cellule Chiuse Closed Cells
 Colore Color		Nero / Black
 Densità Density	ISO 845	130 ± 25 kg/m ³
 Carico Deformazione Compression Deflection	ASTM D-1056	25% 40 ± 15 kPa 50% 120 ± 40 kPa
 Compressione Compression Set	ASTM D-1056 23°C, 50% after 24h	≤ 25%
 Assorbimento Acqua Water Absorption	ASTM D-1056	< 5%
 Durezza Hardness	ISO 868	35 ± 6 Sh 00
 Temperatura Temperature	Costante / Constant Intermittente / Intermittent	-40°C / +100°C +120°C
 Resistente a Resistance to	Ozono, abrasioni e agenti atmosferici. Ozone, abrasion and weathering.	
 Certificazioni Certifications	UL94 HBF (5 mm) FVMUSS 302 Passed ≥ 3 mm	
 Norme Ambientali Environmental Protection	REACH RoHS CMRT	